



CONFOR™ EG FOAMS

Material Summary Sheet 50



Offering solutions for a wide range of applications such as...

- Headphones
- AR/VR Headsets
- Smartphone & Tablet
- Laptop/Notebook

CONFOR™ EG Foams

- Highly compliant shock and energy absorbing, strain-rate sensitive, open-cell foam products
- Available in a range of stiffnesses and shapes
- Non-halogenated
- RoHS compliant

TYPICAL PROPERTIES					
PROPERTY	CFNT-EGS	CF-40EG	CF-42EG	CF-45EG	CF-47EG
Density Nominal kg/m³ (lb/ft³) ASTM D3574	83 (5.18)	96.1 (6)	96.1 (6)	96.1 (6)	96.1 (6)
Flammability UL 94	Meets HBF	Listed HF-1 @ 2mm	Listed HF-1 @ 2mm	Listed HF-1 @ 2mm	Listed HF-1 @ 2mm
Ball Rebound % ASTM D3574	<1	<1	<1	<1	<1
Thermal Conductivity – K Value ASTM C518 W/m*K (BTU in/hr ft ² F)	.0039 (0.27)	.0039 (0.27)	.0040 (0.28)	.0040 (0.28)	.0039 (0.27)
Compression Set (%) ASTM D357 22hr @ 22C (72 F), Compressed 50%	<1	<1	<1	<1	<1
Indentation Force Deflection ASTM D3574 Test B1 Modified 25% Deflection for 12" x 12" x 2" sample 22C (72F) @ 50% Relative Humidity (lbf)	10-17	15-28	29-41	42-55	56-70
Tensile Strength kPa (psi) ASTM D3574 5.1mm/min (20 in/min)	48 (6.7)	53 (7.7)	90 (13)	129 (19)	229 (33)
Tear Strength kN/m (lbf/in) ASTM D3574 5.1 mm/min (20 in/min) @ 22C (72F)	0.28 (1.6)	0.32 (1.8)	0.56 (3.2)	0.63 (3.6)	1.1 (6.5)
Tg (Peak Loss Modulus), °C DMA, 10 Hz & 0.3 amplitude, 30% compression	-2.5	2.7	6.7	14	19
Peak Tan Delta @ Temp C (F) DMA, 10 Hz & 0.3 amplitude, 30% compression	1.34 @ 22 C	1.33 @ 26 C	1.26 @ 30 C	1.17 @ 39 C	1.07 @ 46 C
Compression Load Deflection ASTM D 3574C Modified* Force @ 10% Compression kPa (psi) Force @ 20% Compression kPa (psi) Force @ 30% Compression kPa (psi) Force @ 40% Compression kPa (psi) Force @ 50% Compression kPa (psi) Force @ 60% Compression kPa (psi) Force @ 70% Compression kPa (psi) Force @ 80% Compression kPa (psi)	0.83 (0.12) 1.1 (0.16) 1.2 (0.18) 1.5 (0.22) 1.8 (0.26) 2.4 (0.35) 3.9 (0.57) 9.0 (1.3)	1.65 (0.24) 1.86 (0.27) 2.07 (0.30) 2.41 (0.35) 3.03 (0.44) 4.21 (0.61) 7.58 (1.1) 21.4 (3.09)	2.83 (0.41) 2.90 (0.42) 3.31 (0.48) 3.93 (0.57) 4.96 (0.72) 6.89 (1.04) 13.1 (1.89) 37.9 (5.5)	3.03 (0.44) 3.59 (0.52) 4.0 (0.58) 4.76 (0.69) 6.0 (0.87) 8.96 (1.25) 16.34 (2.37) 51.0 (7.42)	6.89 (1.00) 6.89 (1.00) 7.58 (1.08) 8.96 (1.27) 11.03 (1.60) 15.86 (2.29) 28.96 (4.19) 89.63 (13.0)
RoHS Compliant	Yes	Yes	Yes	Yes	Yes
Halogen Free**	Yes	Yes	Yes	Yes	Yes


The above technical information and data should be considered representative or typical only and should not be used for specification purpose.

*12.7mm thick specimen compressed at a rate of 5.1 mm/min


**Halogen-free per IEC 61249-2-21.




CF-40EG




CF-42EG




CF-45EG



CF-47EG



CFNT-EGS



Technical Information: The technical information, recommendations and other statements contained in this document are based upon tests or experience that Aearo Technologies LLC believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Product Use: Many factors beyond Aearo's control and uniquely within user's knowledge and control can affect the use and performance of an Aearo Technologies LLC product in a particular application. Given the variety of factors that can affect the use and performance of an Aearo Technologies LLC product, user is solely responsible for evaluating the Aearo Technologies LLC product and determining whether it is fit for a particular purpose and suitable for user's method of application.

Warranty, Limited Remedy, and Disclaimer: Unless an additional warranty is specifically stated on the applicable Aearo Technologies LLC product packaging or product literature, Aearo Technologies LLC warrants that each Aearo Technologies LLC product meets the applicable Aearo Technologies LLC product specification at the time Aearo Technologies LLC ships the product. Aearo Technologies LLC MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the Aearo Technologies LLC product does not conform to this warranty, then the sole and exclusive remedy is, at Aearo Technologies LLC's option, replacement of the Aearo Technologies LLC product or refund of the purchase price.

Limitation of Liability: Except where prohibited by law, Aearo Technologies LLC will not be liable for any loss or damage arising from the Aearo Technologies LLC product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.